

DUR-A-WALL

DESCRIPTION

DUR-A-WALL Epoxy Wall System is a pigmented, two component, low odor, 100% thermosetting epoxy formulations. DUR-A-WALL is ideally suited for application on concrete, wood, drywall, cement board or block. This coating is extremely durable, sanitary and easy to clean. A urethane topcoat with a high gloss or satin finish is recommended to provide protection against very aggressive solvents, acids and alcohols. Urethane topcoats are stain resistant and provide a high degree of abrasion resistance.

BENEFITS

- Stain Resistant
- Easy to Clean
- Seamless
- Durable
- Sanitary
- Easy Maintenance

COLORS

DUR-A-WALL is available in 15 standard colors. Please refer to the Standard Color on our website. Custom colors are available upon request.

TYPICAL USES

- Laboratories
- Walk-In Coolers
- Pharmaceutical Plants
- Food Processing Plants
- Commercial Kitchens
- Clean Rooms
- Car Wash Bays
- Hospitals
- Laundries
- Kennels
- Bottling Plants
- Garages
- Warehouses
- Schools
- Locker Rooms

APPLICATION METHOD /SPREAD RATES

DUR-A-GARD pigmented epoxy is used throughout the DUR-A-WALL system for base, grout and seal coats. Typically, DUR-A-GARD epoxy is applied with a 3/8" nap roller at approximately 200 Sq Ft per gallon to yield an even 8 mils wet film thickness with no runs. Coverage will vary depending on porosity and texture of substrate.

LIMITATIONS

This product is best suited for application in temperatures between 55°F and 95°F. Substrate must be clean, sound and dry. Failure to apply the recommended urethane topcoat will result in the system's inability to maintain chemical and abrasion resistance and UV stability.

CLEANING

This product is considered to be a low maintenance coating solution. Please refer to the master Cleaning Guidelines on the website.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Substrate must be clean, sound and dry. Please refer to the master Surface Preparation Guide on our website for more information.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please refer to the master Specifier's Guide for complete three part guide specs in multiple formats.

PACKAGING

DUR-A-WALL Epoxy Wall System is packaged in 1-gallon cans, 5-gallon pails and 50-gallon drums. Shelf life is one year in the original unopened containers.

DUR-A-WALL

TECHNICAL INFORMATION

Toxicity	Non-Toxic, USDA Approved	
Physical Property	Test Method	Result
Hardness, Shore D	ASTM D-2240	70-80
Water Absorption	ASTM D-570	0.04%
Flammability	ASTM D-635	Self-Extinguishing
Flame Spread / NFPA-101	ASTM E-84	Class A
Tensile Strength	ASTM-D 638	3000 psi
Flexural Strength	ASTM D-790	4000 psi
Impact Resistance Alkyd/Latex Paint Dur-A-Wall	ASTM E695-03 (Soft Body Impact)	75 ft.lbs. 0.120" set 75 ft.lbs. 0.060" set
Impact Resistance Alkyd/Latex Paint Dur-A-Wall	USG Pipe Cap Test (Hard Body Impact)	10 ft. lbs. 13 ft. lbs.
Impact Resistance Alkyd/Latex Paint Dur-A-Wall	ASTM D- 2794 @25 inch lbs (Indentation, Mils)	85 68
Bond Strength to Substrates	ASTM D- 4541	Substrate Failure
Thermal Shock, 50 cycles of immersion in Chilled and Boiling water	MIL F 52505	No cracking or loss of adhesion
Abrasion Resistance, CS-17 Wheel, Wgt. Loss 1000 gm. Load 1000 cycles	ASTM D- 4060	15 mg. loss
VOC Content		42.49 g/l

CHEMICAL RESISTANCE

This product is resistant to most common chemicals. Please refer to the master Chemical Resistance Chart on our website for actual resistance to specific chemicals/reagents.

CAUTION

Slight batch-to-batch color variations may occur. When ordering to match a previous color, inquire if the same batch number or quality control number is still available. **Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN.**

Before using any DUR-A-FLEX, Inc. product, be sure the Material Safety Data Sheet is read and understood.