

DUR-A-WALL HP WALL SYSTEM

DESCRIPTION

DUR-A-WALL HP Wall System is a three-step wall coating system designed specifically for areas requiring superior chemical resistance and durability. It starts with a urethane-modified acrylic latex primer followed by two coats of DUR-A-WALL HP TOPCOAT, a pigmented, two-component, low odor urethane formulation. DUR-A-WALL HP is ideally suited for application on concrete, drywall, cement board or block. This coating is extremely durable, chemical resistant, sanitary and easy to clean. DUR-A-WALL HP TOPCOAT with a matte, eggshell or satin finish will provide protection against very aggressive solvents, acids and alcohols. It features up to 10 times the scrubbing durability of traditional epoxy wall coatings and withstands aggressive cleaning regimens such as Vaporized Hydrogen Peroxide.

BENEFITS

- Stain Resistant
- Easy to Clean
- Seamless
- Low Odor
- Chemical Resistant
- CA 01350 Compliant
- Durable
- Sanitary
- Easy Maintenance
- UV Stable
- Scrub Resistant

LIMITATIONS

This product is best suited for application in temperatures between 60°F and 85°F and relative humidity below 75%. Application outside these ranges will impact cure times. Substrate must be clean, sound and dry. **Keep from freezing.**

TYPICAL USES

- Operating Rooms
- Patient Rooms
- Emergency Rooms
- Laboratories
- Pharmaceutical Plants
- Clean Rooms
- Showers

PACKAGING

DUR-A-WALL HP Wall System components are packaged as follows: DUR-A-WALL HP GRIPPER PRIMER – 1-gallon cans, DUR-A-WALL HP BLOCK FILLER – 5-gallon pails, DUR-A-WALL HP TOPCOAT – 2-component pre-measured kits. Shelf life for all products is 1 year with the exception of DUR-A-WALL HP TOPCOAT which is 6 months, in original unopened containers.

COLORS

DUR-A-WALL HP is available in 15 standard colors in three finishes: satin, eggshell and matte. Please refer to the DUR-A-WALL HP Standard Color Chart on our website for color choices. A limited offering of white-based custom colors are available upon request.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Substrate must be clean, sound and dry. Please refer to the Application Instructions for the DUR-A-WALL system being applied for more information.

APPLICATION METHOD /SPREAD RATES

DUR-A-WALL HP GRIPPER PRIMER can be applied with a brush or roller at 200 – 450 SF/gal per, depending on the surface and application method (see Product Data Sheet). DUR-A-WALL HP BLOCK FILLER can be applied with a brush or roller at 150 – 200 SF/gal on masonry block or 200 – 225 SF/gal on porous concrete. DUR-A-WALL HP Topcoat can be applied with a brush or roller at approximately 400 Sq. Ft. per kit (matte, eggshell) and 340 Sq. Ft. per kit (satin).. All coverages will vary depending on porosity and texture of substrate. Refer to the DUR-A-WALL HP Application Instructions for complete application information.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please refer to the Dur-A-Flex website for complete three-part guide specs.

CHEMICAL RESISTANCE

This product is resistant to most common chemicals. Please refer to the Chemical Resistance Chart for actual resistance to specific chemicals/reagents.

CLEANING

This product is considered to be a low maintenance coating solution. Dur-A-Flex recommends cleaning with a heavy-duty alkaline cleaner such as E-Z CLEAN however heavy duty cleaners and disinfectants may be used in harsher environments.

CAUTION

Slight batch-to-batch color variations may occur. When ordering to match a previous color, inquire if the same batch number or quality control number is still available.

Read the Safety Data Sheets for proper personal protective equipment to use when handling this product.

Use only as directed. **KEEP OUT OF REACH OF CHILDREN.**

DUR-A-WALL HP WALL SYSTEM

TECHNICAL INFORMATION

Color	White (can be tinted)		
Flame Spread ASTM E84/NFPA-101	Class A		
Pencil Hardness ASTM D3363	4H Scratch		
Impact Resistance ASTM D2794	140 in. lbs.		
MEK Rubs	>2,000 no noticeable gloss change or degradation		
Pot life, 70° F, 50% R.H.	>2 hours		
Recoat Time	60 - 90 minutes (minimum)		
Recoat Window	Indefinite (sanding recommended)		
Return to Service	16 - 24 hours		
Full Chemical Resistance	7 days (VHP 14 days)		
VOC	HP Topcoat – 0 g/L, Gripper Primer & Block Filler <100 g/L		
	Satin	Eggshell	Matte
Abrasion Resistance, CS-17 wheel, Wt. Loss 1000 gm load, 1000 cycles, ASTM D4060 (mgs loss)	74 mgs	68 mgs	84 mgs
Coverage rates (approx. @ 4mils WFT)	340 SF/kit	400 SF/kit	400 SF/kit

Dur-A-Wall HP Chemical Resistance

Chemical Name	% Conc.	Perf.	Chemical Name	% Conc.	Perf.
Acetic Acid	5%	R	Ethyl Alcohol	200 proof	R
Ammonia, Clear	-	R	Hydrochloric Acid	20%	R
Ammonium Hydroxide	3.1%	R	Hydrogen Peroxide	35%	R
Betadine	-	RS	Isopropyl Alcohol	70%	R
ChloroPrep	-	RS	Lactic Acid	~30%	SS
CIP 200	-	SS	Nitric Acid	70%	N
CIP 300	-	R	Phosphoric Acid	25%	SS
Clorox Concentrate	-	R	Spor-Klenz	-	R
Dur-A-Solve	-	R	Vaporized Hydrogen Peroxide (VHP)	600 ppm	R
Ecolab Cleaner	-	R			

Key: R = Resistant/Recommended N = Not recommended for exposure to material due to coating degradation

RS = Resistant - will not degrade coating but will stain

S = Splashes and spills must be cleaned from surface within 24 hours to avoid coating degradation and staining

SS = Splashes & spills must be cleaned from surface within 24 hours to avoid coating degradation but it will leave stain

All data is based on room temperature exposure. Please check with the Dur-A-Flex Technical Department for elevated constant temperature or thermal shock exposure. Methodology - Coatings were spot tested & checked after 1, 2, & 7 days.

Before using any DUR-A-FLEX, Inc. product, be sure the Safety Data Sheet is read and understood.