

HYBRI-FLEX® MB

DESCRIPTION

HYBRI-FLEX MB is a 100% solids quartz system composed of a 1/8" POLY-CRETE MD SL body coat with a natural quartz broadcast. It uses a 16 mil CRYL-A-GLAZE G201 pigmented broadcast coat, and two 16 mil CRYL-A-TOP T301 pigmented topcoats yielding a total nominal system thickness of 1/4".

BENEFITS

- VOC Compliant
- ADA Compliant
- Contributes to LEED Credits
- CFIA Registered
- Meets USDA, FDA guidelines
- Hygienic - Does Not Harbor Bacteria
- High Chemical Resistance
- High Abrasion Resistance
- Self-Priming for Most Applications
- Wide Service Temperature Range
- Can Be Applied To 5-7 Day Old Concrete

LIMITATIONS

This product is best suited for application in temperatures between 60°F and 85°F. Substrate must be clean, sound and dry.

IMPORTANT: POOL DECK APPLICATIONS

When used for pool deck applications, only the **standard slip-resistant texture** should be used. A 4' x 4' test patch for customer approval prior to installation is highly recommended. Every pool deck installation **must** be registered with a Dur-A-Flex, Inc. Sales representative at the completion of installation and before the pool deck is open for use. These forms can be found in the Technical Catalog in the Master Documents section or in the Contractor Center on our website.

TYPICAL USES

HYBRI-FLEX MB is designed to protect concrete; polymer reinforced screeds, mild steel and water resistant plywood from chemical attack, corrosion, impact and thermal shock. It is also unaffected by freeze/thaw cycles.

- Aesthetic Considerations
- Wet Areas

- Restaurants
- Veterinary Facilities
- Pharmaceutical Plants
- Retail
- Exterior Applications
- Pool Decks

COLORS

Please refer to the Standard Color Chart on our website. Custom colors are available upon request.

PACKAGING & STORAGE CONDITIONS

POLY-CRETE MD SL is available in pre-measured kits that consist of resin, hardener and aggregate. CRYL-A-GLAZE and CRYL-A-TOP resins are packaged in 1-gallon, 5-gallon and 50-gallon quantities.

HYBRI-FLEX MB components must be stored dry. Do not allow resins to freeze. Do not store near open flame or food. The shelf life is 6 months from ship date in the original unopened container.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Surface must be profiled, clean, dry, oil free and sound. Please refer to the Surface Preparation Guide on our website for more information.

APPLICATION METHOD

POLY-CRETE MD SL is applied to a properly prepared area at the required thickness using a "V" notched squeegee. The freshly placed material is then loop rolled into which the proper size aggregate is broadcast to excess to achieve the desired profile. Allow a minimum of 6 hours for the Base Coat to cure before sweeping, sanding or vacuuming. Apply second quartz broadcast into CRYL-A-GLAZE G201. Apply the CRYL-A-TOP pigmented coats to achieve the required finish. CRYL-A-TOP T303 is used for outdoor applications. See Application Instructions on our website for a detailed installation procedure.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please contact DUR-A-FLEX for complete three part guide specs.

HYBRI-FLEX MB

TECHNICAL INFORMATION

Physical Property	Test Method	Result
Percent Reactive		100%
Hardness (Shore D)	ASTM D-2240	88 – 92
Compressive Strength	ASTM C-109	8,300 psi
Tensile Strength	ASTM D-638	2,000 psi
	ASTM D-307	1,350 psi
Tensile Elongation	ASTM D-638	7.50%
Flexural Strength	ASTM D-790	3,700 psi
	ASTM C-580	2,700 psi
Flexural Module of Elasticity	ASTM D-790	4.7×10^5
Linear Expansion	ASTM D-696	3.5×10^{-5}
Bond Strength to Concrete		400 psi substrate fails
Indentation	MIL- D-3134	.025 max
Impact Resistance	ASTM D-2794	>160
Water Absorption	ASTM D-570	0.04%
Heat Resistance Limitation	Intermittent	160°F
	Continuous	140°F
Flammability	ASTM D-635	Self Extinguishing
Abrasion Resistance (CS17 Wheel 1000 GM Load 1000 Cycles)	ASTM D-4060	21 mg.loss
Coefficient of Friction	ASTM D-2047	>0.6
VOC Content		< 100 g/l

DRAWINGS AND DETAILS

Standard CAD drawings and details are available for coves, drains, breaches, transitions, etc. Please refer to the master Drawings and Details guide for actual drawings.

JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website.

MOISTURE CONCERNS

Normal limits for moisture vapor transmission for Hybri-Flex floor systems are 20 lbs./1,000 sq. ft./24 hour using the calcium chloride test per ASTM F-1869 or 99% relative humidity using in-situ Relative Humidity Testing per ASTM F-2170. Please refer to the Floor Evaluation Guidelines at www.dur-a-flex.com for complete details

CHEMICAL RESISTANCE

HYBRI-FLEX MB has excellent resistance to organic and inorganic acids, alkalis, fuel and hydraulic oils, as well as aromatic and aliphatic hydrocarbons. Refer to the Chemical Resistance Chart on our website or consult with our technical staff for non-listed materials.

CLEANING

Regular scrubbing will maintain these systems in serviceable condition. However, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide on our website for more information.

CAUTION

Adequate cross ventilation should be provided. Read, understand and follow Safety Data Sheets and Application Instructions of this flooring system prior to use. Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed.

Before using any DUR-A-FLEX, Inc. product, be sure the Safety Data Sheet is read and understood.