PRODUCT DATA SHEET



95 Goodwin Street East Hartford, CT 06108

Tel: 800-253-3539 • Fax: 860-528-2802 • www.dur-a-flex.com • contact us@dur-a-flex.com

DUR-A-SOLVE

DESCRIPTION

DUR-A-SOLVE is a special combination of aromatic solvents, designed for use as an epoxy thinner. It is specifically formulated for use with DUR-A-GLAZE #4, DUR-A-GLAZE Novolac and, DUR-A-GARD Epoxy Coating. It is an exceptionally efficient solvent for this purpose. Flash point is approximately 85°F as per Closed Cup Test.

Generally, adding 3 - 9% of DUR-A-SOLVE is all that is needed to produce a desired viscosity. Adding DUR-A-SOLVE to a blended epoxy will extend the pot life and the curing time.

IMPORTANT: When DUR-A-SOLVE is used in a Primer Coat, wait 60 minutes or more before proceeding with the next application to permit the solvent to evaporate. Trapping solvent will prevent a proper cure at the bond line, and adhesion failure may result.

PACKAGING

DUR-A-SOLVE is available in 1- gallon cans, 5-gallon pails and 50-gallon drums.

DANGER - USE WITH CAUTION

All solvents may be harmful or fatal if swallowed. These products are flammable or combustible. DUR-A-SOLVE vapors are harmful. Keep away from heat, sparks and open flame. Use only with adequate ventilation and provide an appropriate respirator mask. Avoid skin contact. If contact occurs, wash with soap and water. If splashed into eyes, lift eyelids, flush with clear water for 15 minutes, and call a physician for advice.

Follow the Safety Data Sheet for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN.

Before using any DUR-A-FLEX, Inc. product, be sure the Safety Data Sheet is read and understood.