

HYBRI-FLEX® REFLEXIONS

DESCRIPTION

HYBRI-FLEX REFLEXIONS is a 100% solids low odor, smooth, solid color system; composed of a 8 mil POLY-CRETE TF primer, 1/8" POLY-CRETE MD SL base coat with F-60 quartz broadcast, SHOP FLOOR body coat, DUR-A-GLAZE #4 with REFLEXIONS pigment grout coat, and a 3 mil ARMOR TOP topcoat yielding a total nominal system thickness of 190 mils.

BENEFITS

- Unlimited looks and color variation options
- VOC Compliant
- ADA Compliant
- Contributes to LEED Credits
- Meets USDA, FDA and CFIA standards
- Hygienic - Does Not Harbor Bacteria
- High Chemical Resistance
- High Abrasion Resistance
- Wide Service Temperature Range
- Can Be Applied To 5-7 Day Old Concrete

LIMITATIONS

This product is best suited for application in temperatures between 60°F and 85°F. Substrate must be clean, sound and dry.

TYPICAL USES

- Entries
- Dining Areas
- Lobbies
- Residential
- Reception Areas
- Garages
- Halls / Corridors
- Concourses
- Showrooms
- Retail areas
- Offices
- Bars & lounges
- Fitness Centers

COLORS

HYBRI-FLEX REFLEXIONS is available in variety of colors. Refer to the REFLEXIONS brochure for standard colors.

PACKAGING & STORAGE CONDITIONS

POLY-CRETE MD SL is available in pre-measured kits that consist of resin, hardener and aggregate. SHOP FLOOR and DUR-A-GLAZE #4 epoxy are available in 1 and 5-gallon pails and 50-gallon drums. The fillers are available in 50 lb bags and the aggregate is available in 100 lb bags. ARMOR-TOP is provided in pre-measured kits.

HYBRI-FLEX REFLEXIONS components must be stored dry. Do not allow resins to freeze. Do not store near open flame or food. Every POLY-CRETE product will be shipped with a lot number on the label. The first two digits indicate the year; the second two show the month, the third two indicate the day. The shelf life is 6 months from the date on the label in the original unopened container.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Surface must be profiled, clean, dry, oil free and sound. Please refer to the Surface Preparation Guide on our website for more information.

APPLICATION METHOD

POLY-CRETE MD SL is applied to a properly prepared area at 55 SF/kit using a 1/2" "V" notched squeegee. The freshly placed material is then loop rolled into which F-60 quartz aggregate is broadcast to excess. Allow a minimum of 6 hours for the Base Coat to cure before sweeping. Apply SHOP FLOOR body coat in a color that compliments the GLAZE #4 REFLEXIONS grout coat. Finish with a top coat of clear ARMOR-TOP.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please contact DUR-A-FLEX for complete three part guide specs.

MOISTURE CONCERNS

Normal limits for moisture vapor transmission for Hybri-Flex floor systems are 20 lbs./1,000 sq. ft./24 hour using the calcium chloride test per ASTM F-1869 or 99% relative humidity using in-situ Relative Humidity Testing per ASTM F-2170. Please refer to the Floor Evaluation Guidelines at www.dur-a-flex.com for complete details

HYBRI-FLEX ES

TECHNICAL INFORMATION

Physical Property	Test Method	Result
Hardness (Shore D)	ASTM D-2240	75-80
Compressive Strength	ASTM D-695 ASTM C-579	17,500 psi 12,500 psi
Tensile Strength	ASTM D-638 ASTM C-307	4,000 psi 2,600 psi
Tensile Elongation	ASTM D-638	7.50%
Flexural Strength	ASTM D-790 ASTM C-580	6,250 psi 4,500 psi
Flexural Modulus of Elasticity	ASTM D-790	6.2×10^5
Linear Expansion	ASTM D-696	2×10^{-5}
Bond Strength to Concrete	ASTM D-4541	400 psi substrate fails
Indentation	ML D-3134	.025 MAX
Impact Resistance	ML D-3134	Pass
Water Absorption	ASTM D-570	0.04%
Heat Resistance Limitation		140°F - 200°F
Flammability	ASTM D-635	Self Extinguishing
Flame Spread/NFPA 101	ASTM E-84	Class A
Noise Reduction Coefficient	ASTM C-423	0.05
Taber Abrasion Resistance A&B	ASTM D 4060, 1000g load, 1000 cycles, CS-17 wheel after full cure	<u>Gloss finish</u> <u>Satin finish</u> w/grit - 4 mg. loss w/grit - 8 mg. loss no grit - 10 mg. loss no grit - 12 mg. loss
Coefficient of Friction	ASTM D-2047	>0.6
VOC Content		5 g/l; pigmented Armor Top <100 g/L

CHEMICAL RESISTANCE

HYBRI-FLEX REFLEXIONS has excellent resistance to organic and inorganic acids, alkalis, fuel and hydraulic oils, as well as aromatic and aliphatic solvents. Refer to the Chemical Resistance Chart on our website or consult with our technical staff for non-listed materials.

CLEANING

Regular scrubbing will maintain these systems in serviceable condition. However, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide on our website for more information.

CAUTION

Read, understand and follow Safety Data Sheets and Application Instructions of this flooring system prior to use. Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed

Before using any DUR-A-FLEX, Inc. product, be sure the Safety Data Sheet is read and understood.