

POLY-CRETE TF PLUS COVE HARDENER

DESCRIPTION

POLY-CRETE TF PLUS COVE HARDENER was specifically designed for vertical applications where extra sag resistance is required. Upon mixing, the viscosity drops significantly which makes mixing and handling easy. However, when the mixing blade is removed the viscosity rises once again. This added viscosity makes cove work easier and more efficiently, while maintaining the toughness and chemical resistance found in POLY-CRETE TF.

BENEFITS

- Low Odor
- Coves Close Up Tighter
- Versatile Usage
- Good Chemical Resistance
- Tenacious Bonding Quality

LIMITATIONS

This product is best suited for applications in temperatures between 60°F and 85°F. Substrate must be clean, sound, and dry. Pull excess sealer off with a squeegee to avoid leaving a heavy topcoat on cove base. **POLY-CRETE TF PLUS COVE HARDENER and POLY-CRETE TF PLUS RESIN cannot be mixed with other Poly-Crete resins and hardeners.**

TYPICAL USE

This formula was developed specifically for installing cove and may be used in all phases of that process. (Prime coat, Base coat, and Topcoat)

COLORS

POLY-CRETE TF PLUS COVE HARDENER is mixed with POLY-CRETE TF PLUS RESIN and Aggregate. Please refer to the Poly-Crete color chart for specific colors.

PACKAGING

POLY-CRETE TF PLUS COVE HARDENER is available in pre-measured kits containing POLY-CRETE TF PLUS resin, POLY-CRETE TF PLUS COVE hardener, and one bag of POLY-CRETE TF PLUS aggregate. Flintshot is available in 50 or 100lbs bags.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Substrate must be roughened, clean, sound, and dry. Please refer to the master Surface Preparation Guide on our website for more information.

APPLICATION METHOD

Prime the wall with a coat of the mixed POLY-CRETE TF PLUS resin, POLY-CRETE TF PLUS COVE hardener and POLY-CRETE TF PLUS aggregate. The next step is to trowel a mixture of 10qts of Flintshot aggregate to one mixed kit of resin, hardener, and aggregate. When cured, use a brush to topcoat. Be sure to remove any excess material with a squeegee. This should be done by pulling the material down to the bottom of the cove radius, then back up to the top edge of the cove.

MOISTURE CONCERNS

Please refer to the Floor Evaluation Flow Chart in the Contractor's Center of our website for a step-by-step process to determine the condition of the concrete.

CAUTION

Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN.

POLY-CRETE TF PLUS COVE

TECHNICAL INFORMATION

Cure Time @ 70° F		
Light Traffic	24 hours	
Full Service	3 – 5 days	
Color	10 standard colors	
Mix Ratio (by volume)	3 Component Kit	
Pot Life - 1 gallon @ 77°F	15 minutes	
Adhesion to Concrete	> 400 psi, concrete fails before loss of bond	
Service Temperature	-100 to 220 F (live steam)	
Physical Property	Test Method	Result
Hardness (Shore D)	ASTM D 2240	85
Compressive Strength	ASTM C 579	7,250 psi
Tensile Strength	ASTM D 638	750 psi
Impact Resistance @ 125 mils	ASTM D 1709	> 160 inch lbs
Flexural Strength	ASTM D 790	4,400 psi
VOC Content		0 g/L

Before using any DUR-A-FLEX, Inc. product, be sure the Material Safety Data Sheet is read and understood.