

## **CRYL-A-CHIP - EXTERIOR APPLICATION**

### **GENERAL**

CRYL-A-CHIP is 100% reactive, fast curing, high strength, methyl methacrylate (MMA) based, acrylic flooring system. The nominal 1/16 inch overlay system is composed of a primer, double broadcast of DUR-A-FLEX decorative flakes, and topcoats.

Note: This system cannot be thinned with solvents.

### **COLORS**

CRYL-A-Chip uses DUR-A-FLEX decorative flakes. It is available in standard colors and in two sizes, Micro and Macro. Color options are standard colors and custom color blends. Refer to the CRYL-A-FLEX Color Chart on our website.

### **SURFACE PREPARATION**

The substrate must be dry and free of oil, grease, dirt, bituminous and other contaminants. Unsound concrete and laitance should be removed by appropriate mechanical means. Refer to the DUR-A-FLEX Surface Preparation Guide for detailed instructions on our website.

### **MOISTURE CONCERNS**

Please refer to the Floor Evaluation Flow Chart in the Contractor's Center of our website for a step-by-step process to determine the condition of the concrete.

### **BOND TEST**

Prior to application of the primer, bond tests shall be conducted to determine adequacy of substrate preparation. The bond of the primer to the substrate should be greater than the tensile strength of the substrate. A successful test shows substrate material and sheared aggregate adhering fully to the sample. If only laitance or a small amount of the substrate is attached, further preparation is required. Refer to the Bond Test Guide on our website for more information.

### **VENTILATION**

Prior to any application, proper "negative pressure" ventilation must be established. Refer to the CRYL-A-FLEX Ventilation Guidelines on our website for details.

### **APPLICATION METHOD / SPREAD RATE**

*Read this section, then refer to chart on page 3 for spread rates.*

All MMA resins require the addition of CRYL-A-CURE (BPO) to cure. The proper amount of BPO can be found on the CRYL-A-FLEX Mix Chart on our website. BPO usage is a function of the material and substrate temperature. **Therefore, the temperature of the floor must be measured prior to any mixing or application of material.**

Due to the fast cure of the material, only make enough material that can be properly applied based on floor layout and manpower. A typical batch size of primer or topcoat is usually 1 gallon (4 liters). Hot and /or windy conditions may dictate a smaller batch size. All MMA coats are applied with a brush and roller to achieve an even, puddle free surface. Substrates that are very porous may require an additional primer coat. Roller coats are applied with 3/8 or 1/2-inch (13 mm) nap rollers.

***The application spread rate and material thickness will vary based on wind speed and temperature. Refer to the chart on page 3 to determine the proper rate and thickness.***

Based on the temperature, add the proper amount of BPO to the CRYL-A-PRIME P-101. Mix for 45 seconds or until the BPO is completely dissolved. Pour an even ribbon of material out onto the floor and roll to the proper thickness. The primer coat will cure tack free in 45 - 60 minutes and must be fully cured before applying subsequent coats.

If CRYL-A-BOND is used with primer, the next coat must be applied within 16 hours. Failure to do this could result in inadequate inter-coat adhesion.

The first pigmented (10-12 ounces of CRYL-A-COLOR per gallon) (75 ml per liter) coat of CRYL-A-GLAZE G-201 is roller applied – refer to the chart on page 3. DUR-A-FLEX decorative color chip is broadcast at a rate of 0.1-0.15 lbs per Sq Ft (0.5-0.75 kg per m<sup>2</sup>) into the wet material. Keep Broadcast 6 feet (1.8 m) back from wet edge. After the material has cured, sweep/blow off the excess/loose chips

Apply a second coat of non-pigmented CRYL-A-GLAZE G-201– refer to the chart on page 3 and broadcast the color chips at the same rate. Let the system cure and sweep and vacuum off the excess/loose chips. Brush the surface with a floor buffer of medium stiffness, and vacuum again.

The cured system is top coated with two coats of CRYL-A-TOP T-303 sealer – refer to the chart on page 3 by brush and roller to achieve an even, puddle free surface.

**For proper slip resistance glass beads must be broadcast and back-rolled into the second topcoat at a rate of 1 lb. per 100 square feet. Glass Beads can be purchased at Grainger.com item # (6ZC14).**

**Do not over-dose the Cryl-A-Cure. Excessive BPO will result in discoloration of the topcoat.**

The chart below details the proper mil thickness, spread rates and working time based on wind speed.

Each wet film thickness (WFT) and spread rate indicated on the chart will yield a dry film thickness (DFT) of approximately 16 mils.

The **working time** is the maximum application time available for placement and final back-roll or cross-roll.

This chart is based on a temperature of **70°F**. Working times will be slightly longer at lower temperatures and slightly shorter at higher temperatures.

**Never** apply any material when the temperature is **90°F** or above or the wind speed is higher than 7 mph.

It is important to anticipate if the working area will be exposed to sunlight during the application because a rapid increase in temperature will occur on the substrate.

## **CURE**

CRYL-A-CHIP components will cure in 45-60 minutes. The floor is fully functional one hour after completed application.

**IMPORTANT, DO NOT APPLY THE TOPCOAT TOO THIN.**

It will not cure properly and will pick up dirt and wear prematurely.

## **JOINT GUIDELINES**

Refer to the Joint Guidelines for complete details on our website.

## **PACKAGING**

CRYL-A-CHIP resins are available in 5-gallon (19 liter) pails and 50-gallon (190 liter) drums. CRYL-A-CURE is available in 1-gallon (3.8 liter) cans, 5-gallon (19 liter) pails and 55 lb (25 kg) boxes. DUR-A-FLEX decorative aggregate is available in 50 lb (22.7 kg) bags.

## **STORAGE CONDITIONS**

Store in a cool and dry place below 85 F (30 C), out of direct sunlight. Do not store near open flame or food. The shelf life is 6 months from ship date in the original unopened containers.

## **CAUTION**

**CRYL-A-CHIP resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product.**

Workers should wear protective clothing consisting of splash-proof goggles, impermeable gloves and, where exposure limits are exceeded, an organic vapor respirator should be used. Air powered or explosion proof mixing equipment is required. Adequate cross ventilation should be provided, and if necessary, explosion proof fans may be required. All foodstuffs must be removed during application of the system. **Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN. If substrate and/or material temperature is above 90 F (32 C), Do Not apply material.**

<b>Product &amp; Application</b>	<b>Wind Speed, 70°F</b>	<b>WFT &amp; Spread Rate</b>	<b>Spread Rate over Q-28</b>	<b>Spread Rate over Q-11</b>	<b>Working Time to back-roll</b>
P-101	3 mph	18 mils, 90 square feet per gallon	N/A	N/A	4 minutes
	5 mph	20 mils, 80 square feet per gallon	N/A	N/A	3 minutes
	7 mph	22 mils, 72 square feet per gallon	N/A	N/A	2 minutes
<b> </b>					
G-201 1st broadcast	3 mph	22 mils, 72 square feet per gallon	N/A	N/A	9 minutes
	5 mph	25 mils, 65 square feet per gallon	N/A	N/A	8 minutes
	7 mph	25 mils, 65 square feet per gallon	N/A	N/A	7 minutes
<b> </b>					
G-201 2nd broadcast	3 mph	N/A	65 square feet per gallon	46 square feet per gallon	9 minutes
	5 mph	N/A	60 square feet per gal.	41 square feet per gallon	8 minutes
	7 mph	N/A	60 square feet per gal.	41 square feet per gallon	7 minutes
<b> </b>					
T-303, 1st topcoat	3 mph	N/A	65 square feet per gallon	46 square feet per gallon	10 minutes
	5 mph	N/A	60 square feet per gallon	41 square feet per gallon	9 minutes
	7 mph	N/A	60 square feet per gallon	41 square feet per gallon	7 minutes
<b> </b>					
T-303, 2nd topcoat	3 mph	N/A	72 square feet per gallon	72 square feet per gallon	10 minutes
	5 mph	N/A	65 square feet per gallon	65 square feet per gallon	9 minutes
	7 mph	N/A	65 square feet per gallon	65 square feet per gallon	7 minutes

## **REGISTRATION FORMS**

Every pool deck installation must be registered with a Dur-A-Flex, Inc. Sales representative at the completion of installation and before the pool deck is open for use. These forms can be found in the Technical Catalog in the Master Documents section or on our website.

## **CLEANING**

Warning: Pool decks are predominately wet surfaces that will require daily cleaning with E-Z Clean detergent to aid in the removal of dirt, grime, debris, lotions, soaps and oils. Without a regular maintenance program to remove the accumulation of the above mentioned contaminants, there is an increased risk of slip and fall accidents. To remove hard water deposits (lime scale), periodic use of an acid based cleaner such as "Lime Away" can be used.

Our local sales representative will provide you with a complimentary one gallon sample of E-Z Clean detergent to assist your housekeeping efforts.

For proper cleaning instructions, please refer to our cleaning guidelines in the Contractor Center on our website. Or in our Technical Catalog in the Master Documents section. A floor cleaning training video is also available on our website. Additional quantities of E-Z Clean detergent may be purchased by calling Dur-A-Flex at (800) 253-3539.

### **IMPORTANT!**

*Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet.*

**STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT [DUR-A-FLEX.COM](http://DUR-A-FLEX.COM) FOR THE LATEST VERSION**

**CAUTION!** As with all chemical products, individuals may have different reactions to exposure to specific products. This is dependent upon many factors, including the individual's personal characteristics, the size of the installation, the ventilation available, the intensity of the exposure or the length of the exposure. Individuals may experience discomfort during the installation process of one product, but not another.

In some cases this is experienced as a skin irritation and in others it is experienced as an inhalant irritation. Typically, it disappears once the exposure is eliminated. In some cases people can become "sensitized" to a product and experience the discomfort every time there is exposure without Personal Protective Equipment ("PPE").

To protect yourself from various exposures or discomfort during the mixing and application of our products, we recommend covering exposed skin including, using gloves, long sleeves, safety glasses and a respirator such as the 3M 8577 P95 Universal Disposable Carbon Respirator or a cartridge respirator.

Use only as directed. KEEP OUT OF REACH OF CHILDREN.

Do not reseal moisture-contaminated hardener. This will result in carbon dioxide generation or possible violent rupture of container.