

## **DUR-A-GARD**

### **DESCRIPTION**

DUR-A-GARD Epoxy Coating is a pigmented, two component, low odor, 100% solids, thermosetting epoxy designed especially for flooring applications subjected to moderate traffic and chemicals. DUR-A-GARD Epoxy Coating is ideally suited for application on concrete. This coating is extremely durable, sanitary and easy to clean.

### **“SPECIAL PURPOSE” FORMULATIONS**

1. **DUR-A-GARD “Regular”** has good color stability and a fairly low viscosity so it is easy to apply. However, it is very sensitive to water and moisture during its curing period. The surface must be perfectly dry during application.
2. **DUR-A-GARD “Fast”** is a fast curing hardener designed for fast curing intermediate coats.
3. **DUR-A-GARD “OPF”** is designed to be used as the first and / or second topcoat to yield a uniform “orange peel” finish.
4. **CRETE-GARD** is designed as a topcoat for DUR-A-CRETE, and to achieve a heavy orange peel texture.
5. **DUR-A-GARD “NO SAG”** hardener is used vertical applications.

### **BENEFITS**

- Stain Resistant
- Easy to Clean
- Durable

### **LIMITATIONS**

This product is best suited for application in temperatures between 60°F and 90°F. Substrate must be clean, sound, and dry. Excess of 30 mils may result in bubbles and or pinholes in the coating.

### **TYPICAL USES**

- Laboratories
- Hospitals
- Pharmaceutical Plants
- Clean Rooms

### **COLORS**

Dur-A-Gard is available in 15 standard colors. Please refer to the Standard Color Chart on our website. Custom colors are available upon request.

### **SURFACE PREPARATION**

This product requires preparation in order to perform as expected. Substrate must be profiled, clean, sound, and dry.

Substrate must be primed with DUR-A-SHIELD or DUR-A-GLAZE WB. Please refer to the master Surface Preparation Guide on our website for more information.

### **APPLICATION METHOD /SPREAD RATES**

See DUR-A-GARD Application Instructions on our website for complete instructions.

### **GUIDE SPECIFICATIONS**

This product is part of the DUR-A-FLEX family of polymer systems. Complete three part guide specs can be found on our website.

### **DRAWINGS AND DETAILS**

Standard CAD drawings and details are available for coves, drains, breaches, transitions, etc.

### **JOINT GUIDELINES**

Refer to the Joint Guidelines for complete details on our website.

### **MOISTURE CONCERNS**

Normal limits for moisture vapor transmission for epoxy floor systems are 3 lbs./1,000 sq. ft./24 hour using the calcium chloride test per ASTM F-1869 or 75% relative humidity using In-situ Relative Humidity Testing per ASTM F-2170. Please refer to the Floor Evaluation Guidelines at [www.dur-a-flex.com](http://www.dur-a-flex.com) for complete details.

### **CHEMICAL RESISTANCE**

This product is resistant to most common chemicals. Please refer to the master Chemical Resistance Chart on our website for actual resistance to specific chemicals/reagents.

### **CLEANING**

This product is considered to be a low maintenance flooring solution, however, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide on our website.

### **CAUTION**

Slight lot-to-lot color variations may occur. When ordering to match a previous color, inquire if the same lot number or quality control number is still available. **Follow the Hazardous Materials Identification System labeling guide**

for proper personal protective equipment to use when handling this product. Use only as directed. **KEEP OUT OF REACH OF CHILDREN.**

<b>DUR-A-GARD</b>		
TECHNICAL INFORMATION		
Mix Ratio (by volume)	1 Part Hardener to 2 Parts Resin	
Viscosity at 70°F	700 cps	
Pot Life at 70°F	20 Minutes Regular Hardener 13 Minutes Fast Hardener	
Cure Time, Touch Dry at 70°F	6-8 Hours	
Cured Film Thickness	16 Mills at 100 Sq. Ft. / Gallon Spread Rate	
Toxicity	Non-Toxic	
<b>Physical Property</b>	<b>Test Method</b>	<b>Result</b>
Hardness (Shore D)	ASTM D-2240	70-80
Compressive Strength	ASTM D-695 ASTM C-579	16,000 psi 10,500 psi
Tensile Strength	ASTM D-638 ASTM C-307	3,000 psi 1,950 psi
Tensile Elongation	ASTM D-638	7.50%
Flexural Strength	ASTM D-790 ASTM C-580	4,000 psi 2,900 psi
Flexural Modulus of Elasticity	ASTM D-790	5.5 x 10 <sup>5</sup>
Linear Expansion	ASTM D-696	2 x 10 <sup>-5</sup>
Bond Strength to Concrete	ASTM D-4541	400 psi substrate fails
Indentation	MIL D-3134	.025 MAX
Impact Resistance	MIL D-3134	Pass
Water Absorption	ASTM D-570	0.04%
Heat Resistance Limitation		140°F - 200°F
Flammability	ASTM D-635	Self Extinguishing
Flame Spread/NFPA 101	ASTM E-84	Class A
Abrasion Resistance CS17 Wheel 1000 GM Load 1000 Cycles	ASTM D-4060	35 mg loss
Coefficient of Friction	ASTM D-2047	>0.6
VOC Content		Regular, Fast, Crete Gard = 4 g/l Dur-A-Gard OPF = 59 g/l

**IMPORTANT!**

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet & Application Instructions for important safety information.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT [DUR-A-FLEX.COM](http://DUR-A-FLEX.COM) FOR THE LATEST VERSION