

DUR-A-WALL HP PLUS WALL SYSTEM

DESCRIPTION

DUR-A-WALL HP PLUS Wall System is a multi-step wall coating system designed specifically for areas requiring superior chemical resistance and durability. DUR-A-WALL HP PLUS Wall System consists of a urethane-modified acrylic latex primer (or block filler if needed), one or two DUR-A-GARD NO-SAG EPOXY base coats and two coats of DUR-A-WALL HP TOPCOAT. DUR-A-WALL HP TOPCOAT is a pigmented, two-component, low odor, urethane formulation. DUR-A-WALL HP PLUS is ideally suited for application on concrete, drywall, cement board or block. This coating is extremely durable, sanitary and easy to clean. DUR-A-WALL HP TOPCOAT with a matte, eggshell, or satin finish will provide protection against very aggressive solvents, acids and alcohols. It features up to 10 times the scrubbing durability of traditional epoxy wall coatings and withstands aggressive cleaning regiments such as Vaporized Hydrogen Peroxide.

BENEFITS

- Stain Resistant
- Easy to Clean
- Seamless
- Chemical Resistant
- Easy Maintenance
- Scrub Resistant
- Durable
- Sanitary
- Low Odor
- CA 01350 Compliant
- UV Stable

LIMITATIONS

This product is best suited for application in temperatures between 60°F and 85°F and relative humidity below 75%. Application outside these ranges will impact cure times. Substrate must be clean, sound and dry. **Keep from freezing.**

TYPICAL USES

- Operating Rooms
- Patient Rooms
- Emergency Rooms
- Laboratories
- Pharmaceutical Plants
- Clean Rooms
- Showers

COLORS

DUR-A-WALL HP is available in 15 standard colors in a matte, eggshell, or satin finish. Please refer to the DUR-A-WALL HP

Standard Color Chart on our website. A limited offering of white-based custom colors is available upon request.

PACKAGING

DUR-A-WALL HP PLUS Wall System components are packaged as follows: DUR-A-WALL HP GRIPPER PRIMER – 1-Gallon pails, DUR-A-WALL HP BLOCK FILLER (if req'd) – 5-gallon pails, DUR-A-GARD NOSAG EPOXY – 1- and 5-gallon pails and 50-gallon drums, DUR-A-WALL HP TOPCOAT – 2-component premeasured kits, approximately 400 Sq. Ft. per kit (matte, eggshell) and 340 Sq. Ft. per kit (satin).. Shelf life for all products is 1 year with the exception of DUR-A-WALL HP TOPCOAT which is 6 months, in original unopened containers.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Substrate must be clean, sound and dry. Please refer to the Application Instructions for the DUR-A-WALL PLUS wall system for more information.

APPLICATION METHOD /SPREAD RATES

DUR-A-WALL HP GRIPPER PRIMER can be applied with a brush or roller at 200 – 450 SF/gal depending on the surface and application method (see Product Data Sheet). DUR-A-GARD NO-SAG epoxy is applied with a 3/8" nap roller at approximately 200 - 250 Sq Ft per gallon to yield an even 8 mils wet film thickness. DUR-A-WALL HP Topcoat can be applied with a brush or roller. All coverages will vary depending on porosity and texture of substrate. Refer to the DUR-A-WALL HP PLUS Application Instructions for complete application information.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please refer to the Dur-A-Flex website for complete three-part guide specs.

CHEMICAL RESISTANCE

This product is resistant to most common chemicals. Please refer to the Chemical Resistance Chart for actual resistance to specific chemicals/reagents.

CLEANING

This product is considered to be a low maintenance coating solution. Dur-A-Flex recommends cleaning with a heavy-duty alkaline cleaner such as E-Z CLEAN however heavy

duty cleaners and disinfectants may be used in harsher environments. Refer to the Chemical Resistance Chart for compatibility.

DUR-A-WALL HP PLUS WALL SYSTEM			
TECHNICAL INFORMATION			
Color	White (can be tinted)		
Flame Spread ASTM E84/NFPA-101	Class A		
Pencil Hardness ASTM D3363	4H Scratch		
Impact Resistance ASTM D2794	140 in. lbs.		
MEK Rubs	>2,000 no noticeable gloss change or degradation		
Pot Life, 70°F, 50% RH	>2 hours		
Recoat Time	60-90 minutes (minimum)		
Recoat Window	Indefinite (sanding recommended)		
Return to Service	16-24 hours		
Full Chemical Resistance	7 days (VHP 14 days)		
VOC	HP Topcoat - 0 g/L, Gripper Primer & Block Filler - <100 g/L		
Abrasion Resistance, CS-17 wheel, Wt. Loss 1000 mg load, 1000 cycles, ASTM D4060 (mgs loss)	Satin	Eggshell	Matte
	74 mgs	68 mgs	84 mgs
Coverage Rates (approx. @4 WFT)	340 SF/kit	400 SF/kit	400 SF/kit

DUR-A-WALL HP PLUS CHEMICAL RESISTANCE					
Chemical Name	% Conc.	Perf.	Chemical Name	% Conc.	Perf.
Acetic Acid	5%	R	Ethyl Alcohol	200 proof	R
Ammonia, Clear	-	R	Hydrochloric Acid	20%	R
Ammonium Hydroxide	3.1%	R	Hydrogen Peroxide	35%	R
Betadine	-	RS	Isopropyl Alcohol	70%	R
ChloroPrep	-	RS	Lactic Acid	~30%	SS
CIP 200	-	SS	Nitric Acid	70%	N
CIP 300	-	R	Phosphoric Acid	25%	SS
Clorox Concentrate	-	R	Spor-Klenz	-	R
Dur-A-Solve	-	R	Vaporized Hydrogen Peroxide (VHP)	600 ppm	R
Ecolab Cleaner	-	R			

Key: **R**= Resistant/Recommended **N**= Not Recommended for exposure to material due to coating degradation
RS= Resistant - will not degrade coating but will stain
S= Splashes and spills must be cleaned from surface within 24 hours to avoid coating and staining
SS= Splashes and spills must be cleaned from surface within 24 hours to avoid coating degradation but it will leave a stain

All data is based on room temperature exposure. Please check with the Dur-A-Flex Technical Department for elevated constant temperature or thermal shock exposure. Methodology - Coatings were spot tested & checked after 1, 2, & 7 days.

IMPORTANT!

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet & Application Instructions for important safety information.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT **DUR-A-FLEX.COM** FOR THE LATEST VERSION