

## ACCELERA BP

### **IMPORTANT REMINDER: USE PERSONAL PROTECTION EQUIPMENT AND VENTILATION!**



Use the required PPE for installing Accelera: Carbon Dust Mask or respirator, safety glasses, long sleeve shirt, long pants, gloves, and work boots. Fresh, moving air is essential to a safe working environment when applying resinous flooring products.

### **DESCRIPTION**

ACCELERA BP is a special liquid additive that promotes the bonding of ACCELERA EXT coatings to existing ACCELERA floor systems.

### **FEATURES**

- Increases adhesion to existing ACCELERA floors
- Allows for a fast, low odor “refresh”
- Easily added in the field

### **LIMITATIONS**

ACCELERA BP is used as a bonding agent in situations where the recoat window of an ACCELERA application has passed. **It must be used with ACCELERA EXT resin only.** Use of this product is not a substitute for adequate surface preparation. Please refer to the “Surface Preparation Guide” for more information. This product is best suited for application in temperatures between 60°F and 85°F (maximum) and when jobsite relative humidity is between 30% and 65%.

### **PACKAGING**

ACCELERA BP is available in 16 oz. containers.

### **FLOOR PREPARATION**

Sand with a minimum 100 grit screen or grind to completely de-gloss floor. Vacuum and tack-rag with acetone then verify that the floor is completely de-glossed. **NOTE: For proper adhesion the floor must be completely de-glossed.** Allow floor to dry before applying coating.

### **MIXING INFORMATION**

Add 1.5 oz. of ACCELERA BP to a Large-size ACCELERA EXT resin and mix immediately for 15 seconds - **immediately** followed by the addition of the hardener. Mix for an additional 30 seconds. Follow this sequence for each kit.

#### **IMPORTANT:**

- RESIN AND BP ADDITIVE MUST BE PREMIXED IMMEDIATELY BEFORE ADDING HARDENER
- DO NOT ALLOW BP ADDITIVE TO SIT IN THE RESIN (mixed or unmixed) AS IT WILL BEGIN TO REACT.

**Re-Coat window over ACCELERA Topcoats**

<b>Topcoat</b>	<b>Temp/RH</b>	<b>60%</b>	<b>50%</b>	<b>30%</b>
<b>ACCELERA</b>	85°	12 hrs.	12 hrs.	24 hrs.
	70°	12 hrs.	12 hrs.	24 hrs.
	50°	24 hrs.	24 hrs.	24 hrs.
<b>ACCELERA LH</b>	85°	8 hrs.	12 hrs.	16 hrs.
	70°	8 hrs.	16 hrs.	24 hrs.
	50°	24 hrs.	24 hrs.	24 hrs.
<b>ACCELERA EXT</b>	85°	12 hrs.	12 hrs.	24 hrs.
	70°	12 hrs.	12 hrs.	24 hrs.
	50°	24 hrs.	24 hrs.	24 hrs.
For reference only - refer to LIMITATIONS for min/max temp and RH				

**IMPORTANT!**

*Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet & Application Instructions for important safety information.*

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT **DUR-A-FLEX.COM** FOR THE LATEST VERSION