

CRYL-A-CHIP

GENERAL

CRYL-A-CHIP is 100% reactive, fast curing, high strength methyl methacrylate (MMA) based acrylic flooring system. It is designed to provide a terrazzo like appearance with the benefits of a seamless floor. It is a nominal 1/32 to 1/16 inch (0.8 to 1.6 mm) thick system composed of primer, double broadcast of MICRO or MACRO decorative chips and topcoats. Surface finish can be smooth or slip resistant. This system cannot be thinned with solvents.

COLORS

CRYL-A-CHIP is available in MICRO or MACRO decorative chips. The chips are available in standard or custom color blends.

TYPICAL USES

- Laboratories
- Traffic Aisles
- Rest Rooms
- Lobbies
- Concourse
- Pharmaceuticals
- Manufacturing Areas
- Locker Rooms
- Retail
- Clean Rooms

SURFACE PREPARATION

The substrate must be dry and free of oil, grease, dirt, bituminous and other contaminants. Unsound concrete and laitance should be removed by appropriate mechanical means. Please refer to the DUR-A-FLEX Surface Preparation Guide on our website for detailed instructions.

MOISTURE CONCERNS

Please refer to the Floor Evaluation Flow Chart in the Contractor's Center of our website for a step-by-step process to determine the condition of the concrete.

BOND TEST

Prior to full application of the primer, bond tests shall be conducted to determine adequacy of substrate preparation. The bond of the primer to the substrate should be greater than the tensile strength of the substrate. A successful test shows substrate material and sheared aggregate adhering fully to the sample. If laitance or a small amount of the substrate is attached, further preparation is required. Refer to the Bond Test Guide on our website for more information.

VENTILATION

Prior to any application, proper "negative pressure" ventilation must be established. Refer to the CRYL-A-FLEX Ventilation Guidelines on our website for details.

APPLICATION METHOD / SPREAD RATE

All MMA resins require the addition of CRYL-A-CURE (BPO) to cure. To determine the correct amount of BPO necessary, refer to the CRYL-A-FLEX Mixing Chart. BPO usage is a function of the material and substrate temperature. **Therefore, the temperature of the floor must be measured prior to any mixing or application of material.** Due to the fast cure of the material, only make enough material to be applied in 5 minutes. A typical batch size of primer or topcoat is usually 1 gallon (4 liters). Warmer conditions may dictate a smaller batch size. The primer is applied with a brush or roller at 80 - 100 sq ft per gallon (2-3 m² per liter) to achieve an even, puddle free surface. Substrates that are very porous may require an additional coat. Rough surfaces and holes must be patched with the appropriate CRYL-A-FLEX system before the body coat is applied. Based on the temperature, add the proper amount of BPO to the CRYL-A-PRIME. Mix for 30 - 60 seconds or until the BPO is completely dissolved. Pour an even ribbon of material out onto the floor and roll to the proper thickness. The primer will cure tack free in 45 - 60 minutes.

The first coat of CRYL-A-GLAZE is roller applied at 80 - 100 sq ft per gallon (1.9 - 2.4 m² per liter). DUR-A-FLEX decorative color chip is broadcast at a rate of 0.1 (macro) - 0.15 (micro) lbs per sq ft (0.5-0.75 kg per m²) into the wet material. Keep Broadcast 6 feet (1.8 m) back from wet edge. After the material has cured, sweep/blow off the excess/loose chips.

Apply a second coat of CRYL-A-GLAZE at 80-100 sq ft per gallon (1.9-2.4 m² per liter) and broadcast the color chips at the same rate. Let the system cure and sweep and vacuum off the excess/loose chips. Brush the surface with a floor buffer of medium stiffness, and vacuum again.

The first of two topcoats of CRYL-A-TOP is applied at 90 - 100 sq ft per gallon (2.2 - 2.4 m² per liter). After the material has cured, sand with a floor buffer and 80 or 100 grit paper or screens to achieve desired texture. For additional slip resistance aluminum oxide can be broadcast into the first wet topcoat at a ratio of 1.5-2 lbs per 100 Sq Ft (0.07-0.7 per m²).

A second topcoat of CRYL-A-TOP is applied at 90 - 100 sq ft per gallon (2.2 – 2.4 m² per liter).

CURE

CRYL-A-CHIP components will cure typically in 45-60 minutes. The floor is fully functional one hour after completed application. **IMPORTANT, DO NOT APPLY THE TOPCOAT TOO THIN.** It may not cure properly, it will pick-up dirt and wear pre-maturely.

PACKAGING

CRYL-A-CHIP resins are available in 5-gallon pails and 50-gallon drums. CRYL-A-CURE is available in 1-gallon cans, 5-gallon pails and 55 lb boxes. DUR-A-FLEX decorative chip is available in 10 lb or in 40 lb boxes.

JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website.

TECHNICAL INFORMATION

CRYL-A-CHIP is part of a family of special repair and wearing materials supplied by DUR-A-FLEX. If you require further information on this or any of our other products please contact our Technical Department.

CLEANING

This product is considered to be part of a low maintenance flooring solution, however, certain textures and service environments require specific procedures. Always apply the material at the recommended spread rate. Please refer to the master Cleaning Guide on our website.

STORAGE CONDITIONS

Store in a cool and dry place below 85°F (30°C), out of direct sunlight. Do not store near open flame or food. The shelf life is 6 months from ship date in the original unopened containers.

CAUTION

CRYL-A-CHIP resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product. Workers should wear protective clothing consisting of splash-proof goggles, impermeable gloves and, where exposure limits are exceeded, an organic vapor respirator should be used. Air powered or explosion proof mixing equipment is required. Adequate cross ventilation should be provided, and if necessary, explosion proof fans may be required. All foodstuffs must be removed during application of the system. **Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN. If substrate and/or material temperature is above 90°F (32°C), Do Not apply material. Detailed application instructions should be obtained, read and understood prior to commencement of application.**

IMPORTANT!

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT DUR-A-FLEX.COM FOR THE LATEST VERSION

CAUTION! As with all chemical products, individuals may have different reactions to exposure to specific products. This is dependent upon many factors, including the individual's personal characteristics, the size of the installation, the ventilation available, the intensity of the exposure or the length of the exposure. Individuals may experience discomfort during the installation process of one product, but not another.

In some cases this is experienced as a skin irritation and in others it is experienced as an inhalant irritation. Typically, it disappears once the exposure is eliminated. In some cases people can become "sensitized" to a product and experience the discomfort every time there is exposure without Personal Protective Equipment ("PPE").

To protect yourself from various exposures or discomfort during the mixing and application of our products, we recommend covering exposed skin including, using gloves, long sleeves, safety glasses and a respirator such as the 3M 8577 P95 Universal Disposable Carbon Respirator or a cartridge respirator.

Use only as directed. **KEEP OUT OF REACH OF CHILDREN.**

Do not reseal moisture-contaminated hardener. This will result in carbon dioxide generation or possible violent rupture of container.