

CRYL-A-FLOOR

GENERAL

CRYL-A-FLOOR is a high strength, 100% reactive, fast curing, methyl methacrylate (MMA) based, acrylic flooring system. It is composed of a primer, double broadcast of aggregates, and finished with pigmented topcoat(s) for a slip resistant system with a nominal thickness of 1/8 inch.

Note: This system cannot be thinned with solvents.

COLORS

CRYL-A-FLOOR is available in assorted standard colors. Please refer to the Standard Color Chart on our website. Custom colors are available upon request.

TYPICAL USES

- Laboratories
- Manufacturing Areas
- Traffic Aisles
- Food Processing Areas
- Heavy Industry
- Bottling Areas
- Walk In Coolers
- Freezers
- Loading Docks

SURFACE PREPARATION

The substrate must be dry and free of oil, grease, dirt, bituminous and other contaminants. Unsound concrete and laitance should be removed by appropriate mechanical means. Refer to the DUR-A-FLEX Surface Preparation Guide for more information.

MOISTURE CONCERNS

Please refer to the Floor Evaluation Flow Chart in the Contractor's Center of our website for a step-by-step process to determine the condition of the concrete.

BOND TEST

Prior to full application of the primer, bond tests shall be conducted to determine adequacy of substrate preparation. The bond of the primer to the substrate should be greater than the tensile strength of the substrate. A successful test shows substrate material and sheared aggregate adhering fully to the sample. If only laitance or a small amount of the substrate is attached, further preparation is required. Refer to the Bond Test Guide for more information.

VENTILATION

Prior to any application, proper "negative pressure" ventilation

must be established. Please refer to the CRYL-A-FLEX Ventilation Guidelines for details.

APPLICATION METHOD / SPREAD RATE

All MMA resins require the addition of CRYL-A-CURE (BPO) to cure. To determine the correct amount of BPO necessary, refer to the CRYL-A-FLEX Mixing Chart. BPO usage is a function of the material and substrate temperature. **Therefore, the temperature of the floor must be measured prior to any mixing or application of material.**

Due to the fast cure of the material, only make enough material to be applied in 5 minutes. A typical batch size of primer or topcoat is usually 1 gallon (4 liters). Warmer conditions may dictate a smaller batch size. The primer is applied with a brush or roller at 80 - 100 sq ft per gallon (2 - 2.5 m² per liter) to achieve an even, puddle free surface. Substrates that are very porous may require an additional coat. Rough substrates may require a longer nap to avoid puddles. Rough surfaces and holes must be patched with the appropriate CRYL-A-FLEX system before the body coat is applied. Based on the temperature, add the proper amount of BPO to the CRYL-A-PRIME P-101. Mix for 30 - 60 seconds or until the BPO is completely dissolved. Pour an even ribbon of material out onto the floor and roll to the proper thickness. The primer will cure tack free in 45 - 60 minutes.

If CRYL-A-BOND is used with primer, the next coat must be applied within 16 hours. Failure to do this could result in inadequate inter-coat adhesion.

The first coat of pigmented CRYL-A-GLAZE G-201 is roller applied at 80 - 100 Sq Ft per gallon (2.0 - 2.5 m² per liter). Aggregate is broadcast at an approximate rate of 0.3-0.5 lbs per sq ft (0.45-0.75 kg per m²). **Do not over broadcast, only apply enough sand to cover the wet resin**, over broadcasting can result in the resin not curing properly. Keep broadcast 6 feet (1.8 meters and below) back from the wet working edge, as this will make it easier for the roller man. Let material cure and sweep off excess aggregate. When broadcasting aggregate, make sure to throw it high and let it "rain down" into the surface. Do not throw at an angle as this can result in ripples.

Note: For aggregate, a double broadcast with Q-28 sand

will yield a 1/8 inch (3 mm) thick floor. A double broadcast with Q-11 will yield a 3/16 (4.75 mm) thick floor. The Q-11 (thicker) floor should be used in areas that are exposed to impact, i.e. dropping of tools and/or heavy equipment use.

The second coat of pigmented CRYL-A-GLAZE G-201 is roller applied at 80-100 Sq Ft per gallon (2.0 - 2.5 m² per liter) with Flinshot sand and 70 – 90 sq ft per gallon (1.7 - 2.2 m² per liter) with Q-Rok. Aggregate is broadcast at 0.4-0.5 lbs per sq ft (0.6-0.75 m² per kg). Let material cure and again remove all excess aggregate.

The cured system is top-coated with two coats of CRYL-A-TOP T-301. The first topcoat is applied by roller at 60 – 80 sq ft per gallon with Flinshot sand or 50 -70 sq ft per gallon with Q-Rok. The second topcoat is applied by roller at 80 – 100 sq ft per gallon with flinshot sand or 70 - 90 sq ft per gallon with Q-Rok. If a smoother finish is required, the surface may be sanded before the second topcoat is applied.

CURE

CRYL-A-FLOOR components will typically cure in 45-60 minutes. The floor is fully functional one hour after completed application. **IMPORTANT, DO NOT APPLY THE TOPCOAT TOO THIN.** It may not cure properly, it will pick up dirt, and it may wear prematurely.

PACKAGING

CRYL-A-FLOOR resins are available in 5-gallon (19 liter) pails and 50-gallon (190 liter) drums. CRYL-A-CURE is available in 1-gallon (3.8 liter) cans, 5-gallon (19 liter) pails and 55 lb (25 kg) boxes. Aggregate is available in 50 lb (22.7 kg) and 100 lb (45 kg) bags.

CLEANING

This product is part of a low maintenance flooring solution, however, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide.

STORAGE CONDITIONS

Store in a cool and dry place below 85°F (30°C), out of direct sunlight. Do not store near open flame or food. The shelf life is 6 months from ship date in the original unopened containers.

JOINT GUIDELINES

Refer to the Joint Guidelines on our website for complete details.

CAUTION

CRYL-A-FLOOR resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product. Workers should wear protective clothing consisting of splash-proof goggles, impermeable gloves and, where exposure limits are exceeded, an organic vapor respirator should be used. Air powered or explosion proof mixing equipment is required. Adequate cross ventilation should be provided and explosion proof fans may be required. All foodstuffs must be removed during application of the system. **Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN. If substrate and/or material temperature is above 90°F (32°C), Do Not apply material. Detailed application instructions should be obtained, read and understood prior to commencement of application.**

IMPORTANT!

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT DUR-A-FLEX.COM FOR THE LATEST VERSION

CAUTION! As with all chemical products, individuals may have different reactions to exposure to specific products. This is dependent upon many factors, including the individual's personal characteristics, the size of the installation, the ventilation available, the intensity of the exposure or the length of the exposure. Individuals may experience discomfort during the installation process of one product, but not another.

In some cases this is experienced as a skin irritation and in others it is experienced as an inhalant irritation. Typically, it disappears once the exposure is eliminated. In some cases people can become "sensitized" to a product and experience the discomfort every time there is exposure without Personal Protective Equipment ("PPE").

To protect yourself from various exposures or discomfort during the mixing and application of our products, we recommend covering exposed skin including, using gloves, long sleeves, safety glasses and a respirator such as the 3M 8577 P95 Universal Disposable Carbon Respirator or a cartridge respirator.
Use only as directed. KEEP OUT OF REACH OF CHILDREN.

Do not reseal moisture-contaminated hardener. This will result in carbon dioxide generation or possible violent rupture of container.