

DUR-A-CHIP DECORATIVE EPOXY FLOORING

IMPORTANT! Read these instructions carefully several days prior to starting your work. Seek answers to any questions you may have before you begin. DUR-A-FLEX, Inc. maintains a Technical Staff that will be glad to answer your questions and give you advice pertaining to your particular installation.

DUR-A-CHIP is applied by broadcast method.

When recommended spread rates are followed, a double broadcast of either MICRO or MACRO decorative chip will produce a nominal system thickness of 60 mils. Surface finish can be smooth or textured for added slip resistance.

SURFACE PREPARATION

Surface must be clean, sound, dry and free of all oil, grease, detergent film, sealers and/or curing compounds. A surface profile of CSP 3 is appropriate for most applications. All paint should be removed unless it is a properly applied, totally de-glossed, high quality epoxy. Upper level rooms, like mechanical rooms, bathrooms, or wet process areas that have space below should receive ELAST-O-COAT seamless fluid applied membrane. Please refer to the DUR-A-FLEX Surface Preparation Guide on our website for detailed instructions. No epoxy coatings should be applied unless surface temperature is a minimum of 5 degrees F above dew point. See Dew Point Calculation Chart on our website for detailed instructions.

NOTE: For each application of material and before mixing, mark your batches to ensure you achieve your spread rate targets. This is best accomplished by dividing your target spread rate by the width of the area being coated (or your planned wet edge). Example: If your spread rate is 100 square feet and your area is 20 feet wide you would make a mark every 5 feet (100 divided by 20 = 5).

MIXING AREA

Select a convenient mix area and protect the surface from spillage by covering with a layer of cardboard and/or sheet of plastic. Be generous with the amount of space you allocate for this function. The more comfortably your mixer works, the less likely you are to have a "mix error". Make ready all necessary tools, mix and measure containers, etc. DO NOT MIX ANY EPOXY UNTIL READY FOR IMMEDIATE USE. Once hardener and resin are combined, it must be used without delay. Apply masking tape wherever coating is intended to stop. To obtain neat, straight, chip resistant edges at termination points and/or drains, a "keyed edge" must be installed.

PRE-PATCH

Pre-patch badly eroded, spalled or cracked areas with the proper material: Use ELAST-O-COAT thickened with NO SAG 1 for moving joints and DUR-A-GLAZE #4 mixed with NO-SAG 2 or Flintshot for non-moving joints. BE SURE TO LEAVE AS LITTLE EXCESS AS POSSIBLE AS IT WILL BE HIGHLIGHTED IN SUCCESSIVE STEPS. Sanding or grinding pre-patch areas will help in hiding deviations.

JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website.

PRIMING

All surfaces must be primed with DUR-A-GLAZE WB Primer, DUR-A-GLAZE MVP Primers*, or ELAST-O-COAT as soon as the surface has been prepared.

*Dur-A-Glaze MVP Primers include any available version of Dur-A-Glaze MVP, MVP2, or MVP3 Primer.

APPLICATION METHOD

- A. Prepare the surface as outlined in the DUR-A-FLEX Surface Preparation Guide.
- B. Measure out 1/2 gallon of DUR-A-GARD OPF hardener and 1 gallon of DUR-A-GARD resin. When combining, be sure to add the hardener first. Add the resin and scrape out the container. Be careful to pour both hardener and resin into the center of the mixing pail. Mix the blended epoxy with a slow speed power drill with a Jiffler type mixing blade for 2 minutes. Always scrape the sides and bottom of the measuring bucket to assure thorough blending.
- C. Apply the mixed DUR-A-GARD using a non-shed 18," 3/8 inch nap roller at 300-350 Sq Ft per gallon by the dip and roll method. Back roll with a quality, non-shed roller 18," 3/8 inch nap roller.
- D. Broadcast MICRO or MACRO decorative chip. While wearing spiked shoes, walk on the wet epoxy holding a 2-gallon container and broadcast the decorative chip until the floor appears dry (0.10 lbs per SF for macro and 0.15 lbs per SF for micro chips). Be sure to keep moving while throwing the chips UP into the air so it falls vertically onto the epoxy. **IMPORTANT:** Do not "seed" the edge that will be joining the next section. Be sure to leave a "WET EDGE" (a 24" strip "unseeded" to permit overlapping when proceeding onto next section). Do not walk on the decorative chip with spiked shoes. Be sure to keep any impurities out of the chips such as broom bristles, debris, etc. Allow to cure.
- E. Sweep off the excess decorative chip using a stiff, clean, dry broom with synthetic bristles.
- F. Scrape the floor with a trowel or floor scraper. Sweep and vacuum the floor again.
- G. Measure out 1 part DUR-A-GLAZE #4 hardener and 2 parts DUR-A-GLAZE #4 resin and mix the blended epoxy for 2 minutes. Be sure to follow the procedures outlined in step (B). Mix only what you can apply within 5 - 10 minutes. **NOTE:** Do not use "Fast" Hardeners for topcoats as they yellow very quickly and could produce pinholes.
- H. Apply the mixed DUR-A-GLAZE #4 WATER CLEAR at 100-150 Sq Ft per gallon with a flat squeegee and back roll with a quality 18", 3/8" non-shed roller.
- I. Broadcast MICRO or MACRO decorative chip. Follow procedures outlined in step (D) above. Allow to cure.
- J. Sweep off the excess decorative chip using a stiff, clean, dry broom with synthetic bristles.
- K. Scrape the floor with a trowel or floor scraper. Sweep and vacuum the floor again.
- L. Apply a coat of DUR-A-GLAZE #4 at 100-150 Sq Ft per gallon with a flat squeegee and back roll with a quality 18", 3/8" non-shed roller. Follow the same procedure for mixing as outlined in step (F). For anti-slip properties, back roll Aluminum Oxide #54 to #36 into grout coat.
- M. Apply Armor Top per Product Data Sheet instructions. Remove all masking tape as you proceed, before it gets out of reach. Allow to cure.

IMPORTANT: Be sure to pour the hardener into the mixing bucket first, when working with the epoxy and vice versa when working with the urethane. Always scrape the sides and bottom of mixing container to assure thorough blending. USE SIGNS AND BARRIERS to keep traffic out of the area. Do not allow any water on coated surface for 24-48 hours. Chemical spillage must be prevented for approximately 5 days.

NOTE: Use DUR-A-SOLVE or a Xylene for clean up.

IMPORTANT!

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT DUR-A-FLEX.COM FOR THE LATEST VERSION

CAUTION! As with all chemical products, individuals may have different reactions to exposure to specific products. This is dependent upon many factors, including the individual's personal characteristics, the size of the installation, the ventilation available, the intensity of the exposure or the length of the exposure. Individuals may experience discomfort during the installation process of one product, but not another.

In some cases this is experienced as a skin irritation and in others it is experienced as an inhalant irritation. Typically, it disappears once the exposure is eliminated. In some cases people can become "sensitized" to a product and experience the discomfort every time there is exposure without Personal Protective Equipment ("PPE").

To protect yourself from various exposures or discomfort during the mixing and application of our products, we recommend covering exposed skin including, using gloves, long sleeves, safety glasses and a respirator such as the 3M 8577 P95 Universal Disposable Carbon Respirator or a cartridge respirator.

Use only as directed. KEEP OUT OF REACH OF CHILDREN.

Do not reseal moisture-contaminated hardener. This will result in carbon dioxide generation or possible violent rupture of container.