

DUR-A-GARD 50/50

DESCRIPTION

DUR-A-GARD 50/50 epoxy coating is a pigmented, two component, low odor, 100% solids, thermosetting epoxy designed especially for flooring applications subjected to moderate traffic and chemicals. This coating is extremely durable, sanitary and easy to clean. The high gloss, finish is stain-resistant and virtually unaffected by oil, grease, gasoline, strong detergents and salt.

BENEFITS

- Stain Resistant
- Easy to Clean
- Durable

LIMITATIONS

This product is best suited for application in temperatures between 60°F and 90°F. This product is not to be used to broadcast into or as a grout coat over aggregate. Excess of 30 mils will result in bubbles and or pinholes in the coating. Some light colors may require multiple coats for adequate hiding power. Certain colors appear white when scratched. Smoke Blue should be top coated with POLY-THANE 2 HIGH SOLIDS with ADD-A-COLOR or ARMOR TOP to reduce the “White” appearance of scratches.

TYPICAL USES

- Laboratories
- Automotive
- Pharmaceutical
- Clean Rooms
- Hospitals
- Laundries
- Kennels
- Manufacturing

COLORS

DUR-A-GARD 50/50 is available in 15 standard colors. Please refer to the Standard Color Chart on our website. Custom colors are available upon request.

PACKAGING

DUR-A-GARD 50/50 epoxy coating is packaged in 1-gallon cans and 5-gallon pails. Shelf life is one year in unopened containers.

SURFACE PREPARATION

The substrate must be dry and free of oil, grease, dirt, and other contaminants. Unsound concrete and laitance should be removed by appropriate mechanical means. Refer to the Surface Preparation Guidelines on our website.

APPLICATION METHOD/SPREAD RATES

DUR-A-GARD 50/50 is applied with a 3/16” squeegee and roller at approximately 100 Sq Ft per gallon. See the DUR-A-GARD 50/50 Application Instruction Sheet for complete instructions.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please contact DUR-A-FLEX for complete three part guide specs.

DRAWINGS AND DETAILS

Standard CAD drawings and details are available for coves, drains, breaches, transitions, etc. Please contact DUR-A-FLEX for actual drawings.

JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website.

MOISTURE CONCERNS

Please refer to the Floor Evaluation Guidelines in the Contractor’s Center of our website for a step-by-step process to determine the condition of the concrete.

CHEMICAL RESISTANCE

This product is resistant to many common chemicals. For actual resistance to specific chemicals please refer to the master Chemical Resistance Chart on our website.

CLEANING

This product is considered to be a low maintenance flooring solution; however, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide on our website at Cleaning Guide.

HARDENER FORMULATIONS

1. **DUR-A-GARD 50/50 “Regular”** is low viscosity so it is easy to apply. However, it is very sensitive to water and moisture during its curing period. The surface must be perfectly dry during application.
2. **DUR-A-GARD 50/50 “Fast”** is a fast curing hardener - but cannot be topcoated with any other performance topcoat. (that coating will not bond)

DUR-A-GARD 50/50

TECHNICAL INFORMATION

Color	Available in Standard & Special Colors	
Mix Ratio (by volume)	1 part hardener to 2 parts resin	
Viscosity at 70°F	1250 cps	
Pot Life at 70°F	20 minutes regular hardener, 13 minutes fast hardener	
Cure Time, Touch Dry at 70°F	8 hours regular, 4 hours fast	
Cured Film Thickness	16 mils at 100 sq. ft / Gallon spread rate	
Toxicity	Non-toxic, USDA Approved	
Physical Property	Test Method	Result
Hardness (Shore D)	ASTM D-2240	70-80
Compressive Strength	ASTM D-695 ASTM C-579	16,000 psi 10,500 psi
Tensile Strength	ASTM D-638 ASTM C-307	3,000 psi 1,950 psi
Tensile Elongation	ASTM D-638	7.50%
Flexural Strength	ASTM D-790 ASTM C-580	4,000 psi 2,900 psi
Flexural Modulus of Elasticity	ASTM D-790	5.5 x 10 ⁵
Linear Expansion	ASTM D-696	2 x 10 ⁻⁵
Bond Strength to Concrete	ASTM D-4541	400 psi substrate fails
Indentation	MIL D-3134	.025 MAX
Impact Resistance	MIL D-3134	Pass
Water Absorption	ASTM D-570	0.04%
Heat Resistance Limitation		140°F - 200°F
Flammability	ASTM D-635	Self Extinguishing
Flame Spread/NFPA 101	ASTM E-84	Class A
Abrasion Resistance CS17 Wheel 1000 GM Load 1000 Cycles	ASTM D-4060	35 mg loss (without Urethane Topcoat) 4 mg loss (with Armor Top Gloss)
Static Coefficient of Friction*	ANSI B101.1	>0.6
Dynamic Coefficient of Friction - Wet*	ANSI A326.3	>0.42
VOC Content		0 g/L

*Dur-A-Flex flooring systems can be built to meet or exceed the requirements of Static or Dynamic Coefficient of Friction testing per installation. Contact your Dur-A-Flex territory sales manager or tech representative for more information on alternative textures, grit/grip additives, or smooth coatings for your specific environment. A sample should always be obtained and tested prior to purchase for any non-slip flooring system.

IMPORTANT!

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet & Application Instructions for important safety information.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT DUR-A-FLEX.COM FOR THE LATEST VERSION