

DUR-A-GARD NOVOLAC

DESCRIPTION

DUR-A-GARD NOVOLAC is a pigmented two component, highly chemical resistant performance topcoat designed as a final topcoat over smooth coatings. It is designed to provide protection against chemicals, acids, and intermittent high temperature fluctuations.

BENEFITS

- Highly Chemical Resistant: Resistant to a wide range of common chemicals and acids
- Low Odor, Low VOCs: Install in more locations without offensive odors or harmful Volatile Organic Compounds
- High Heat Distortion Threshold: Resistant to intermittent high temperature fluctuations, allowing for installation in harsh environments

COLORS

Available in a selection of standard solid colors. For a full list of available colors please refer to the Standard Color Chart or visit our website for more information.

PACKAGING

DUR-A-GARD NOVOLAC is a resin and a hardener: Pre-Weighted Kit, ~125 sq ft @ 16 mils/kit

COMMON USE SITES

- Pharmaceutical
- Secondary Containment
- Chemical Storage Warehouses
- Plating Lines
- Acid Cleaning Bath Areas
- Pulp & Paper Mills
- Battery Storage

SYSTEM GUIDELINES

Best suited for application between 60°F – 90°F and when the substrate is 5° above dew point.

DUR-A-GARD NOVOLAC is meant to be a final topcoat and should not be coated with any other topcoat.

LIGHT COLOR DUR-A-GARD NOVOLAC MUST BE APPLIED OVER A PIGMENTED PRIMER, MATCHING BROADCAST, AND/OR PIGMENTED GROUT COAT - FAILURE TO DO SO WILL RESULT IN BLOTCHY OR STREAKY COLOR OF THE FINAL SYSTEM.

DUR-A-GARD NOVOLAC CANNOT BE USED AS A GROUT COAT FOR BROADCAST SYSTEMS - PINHOLES WILL OCCUR

DO NOT APPLY DUR-A-GARD NOVOLAC IN EXCESS OF 30 MILS - MAY RESULT IN BUBBLES AND/OR PINHOLES IN THE CURED COATING

If a grout coat/final topcoat is required over a broadcast – refer to DUR-A-GLAZE NOVOLAC instead.

MOISTURE CONCERNS

Normal limits for moisture vapor transmission are 3 lbs./1,000 sq ft /24 hour using the calcium chloride test per ASTM F-1869 or 75% relative humidity using in-situ Relative Humidity Testing per ASTM F-2170. Core Analysis Testing is available from Dur-A-Flex to help provide a measurement of ionic content in flooring substrate. Please refer to the Floor Evaluation Guidelines or visit our website for more information.

CHEMICAL RESISTANCE

This product is resistant to a large amount of chemicals and acids. Please refer to master Chemical Resistance Chart for a full resistance list or visit our website for more information.

SURFACE PREPARATION / JOINT GUIDELINES

Use a shot blaster or surface grinder to achieve a CSP of at least 3, ensure the surface is clean, dry, and free of all contaminants before you begin applying the system. Always honor moving joints and fill static joints as part of the preparation step. Refer to the master Surface Preparation and Joint Guidelines Guide on our website for more information.

SYSTEM APPLICATION

1. Combine pre-weighed kits of Resin and Hardener
2. Apply using a v-notched squeegee followed by back-rolling and cross-rolling
3. Allow to cure for full chemical resistance

MAINTENANCE

This product is considered to be a low maintenance flooring solution; however, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide or visit our website for more information.

DUR-A-GARD NOVOLAC

TECHNICAL INFORMATION

Mix Ratio: Pre-weighed Kits	1 Container of Resin : 1 Container of Hardener
Pot Life at 70°F	30 minutes
Tack Free Time at 70°F (ready for re-coat)	8-10 hours
Cure Time at 70°F	24 hours
Full Cure Time (full chemical resistance)	7 days @ 70°F
Minimum Temperature for Application	60°F
Cured Film Thickness (Spread Rate)	16 mils (~125 sq ft/kit)
Hardness, Shore D	86-90
Heat Resistance Limitation (Intermittent Only)	250°F (122°C)

Physical Property	Test Method	Result
Compressive Strength	ASTM C-579	14,000 psi
Flexural Strength	ASTM C-580	5,500 psi
Tensile Strength	ASTM C-307	2,500 psi
Flexural Modulus of Elasticity	ASTM D-790	1.95 x 10 ⁶ psi
Bond Strength	ACI-403-PP	420 psi (concrete fails)
Indentation	MIL-D 3134-F	No Indentation
Water Absorption	ASTM D-570 ASTM D-696	0.05%, 24 hours in water 2.2 x 10 ⁻⁵ in/in/°F
Abrasion Resistance C-10 Wheel, 1,000 mg load, 1,000 cycles	ASTM D-1044	75 mg weight loss
Flammability	ASTM D-635	Self Extinguishing. Extent of burning less than 0.35 in.
VOC Content		8.5 g/L
Static Coefficient of Friction	ASTM D-2047	>0.6

IMPORTANT!

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet & Application Instructions for important safety information.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT DUR-A-FLEX.COM FOR THE LATEST VERSION