

HYBRI-FLEX AC WITH ACCELERA

DESCRIPTION

HYBRI-FLEX AC w/ACCELERA is a 100% solids low odor decorative chip system. It is composed of a 1/8" POLY-CRETE SL body coat with a decorative chip broadcast; a DUR-A-GLAZE #4 broadcast coat, and two ACCELERA topcoats yielding a total nominal system thickness of 3/16".

BENEFITS

- VOC Compliant
- ADA Compliant
- Contributes to LEED Credits
- Meets USDA, FDA and CFIA Standards
- Hygienic - Does Not Harbor Bacteria
- High Chemical Resistance
- High Abrasion Resistance
- Self-Priming for Most Applications
- Wide Service Temperature Range
- Can Be Applied To 5-7 Day Old Concrete

LIMITATIONS

This product is best suited for application in temperatures between 60°F and 85°F. Substrate must be clean, sound and dry.

TYPICAL USES

HYBRI-FLEX AC w/ACCELERA is designed to be installed over concrete, and is unaffected by thermal cycling.

- Malls
- Hospitals
- Labs
- Commercial Businesses
- Educational Facilities

COLORS

The decorative colored chips that are used in the HYBRI-FLEX AC w/ACCELERA system are available in MACRO and MICRO size. Refer to the Color Selection Chart for the standard chip blends. Customs blends are available.

PACKAGING / STORAGE CONDITIONS

POLY-CRETE SL is available in pre-measured kits that consist of resin, hardener and aggregate. ACCELERA is available in pre-measured kits. The Decorative chips are available in 10lb or 40lb boxes. HYBRI-FLEX AC w/ACCELERA components

must be stored dry. Do not allow resins to freeze. Do not store near open flame or food. The shelf life of this product is 6 months from ship date in the original unopened container.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Surface must be profiled, clean, dry, oil free and sound. Please refer to the Surface Preparation Guide on our website for more information.

APPLICATION METHOD

POLY-CRETE SL is applied to a properly prepared area at the required thickness using a "V" notched squeegee. The freshly placed material is then loop rolled into which the proper size colored chip blend is broadcast to excess to achieve the desired aesthetics. Allow a minimum of 6 hours for the Base Coat to cure before sweeping, sanding or vacuuming. A second chip broadcast is delivered into Dur-A-Glaze #4. Apply the ACCELERA coats to achieve the required finish. See the Application Instructions on our website for a detailed installation procedure.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please contact DUR-A-FLEX for complete three part guide specs.

DRAWINGS AND DETAILS

Standard CAD drawings and details are available for coves, drains, breaches, transitions, etc. Please refer to the master Drawings and Details guide for actual drawings.

JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website.

MOISTURE CONCERNS

Normal limits for moisture vapor transmission for Hybri-Flex floor systems are 20 lbs./1,000 sq. ft./24 hour using the calcium chloride test per ASTM F-1869 or 99% relative humidity using in-situ Relative Humidity Testing per ASTM F-2170. Please refer to the Floor Evaluation Guidelines on our website for complete details.

CHEMICAL RESISTANCE

This product is resistant to many common chemicals. Please

refer to the master Chemical Resistance Chart on our website for actual resistance to specific chemicals/reagents.

CLEANING

Regular scrubbing will maintain these systems in serviceable condition. However, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide on our website for more information.

CAUTION

Read, understand and follow Material Safety Data Sheets and Application Instructions of this flooring system prior to use. Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed.

HYBRI-FLEX AC		
TECHNICAL INFORMATION		
Physical Property	Test Method	Result
60 Gloss	ASTM D-523	90+
Impact Resistance	ASTM D-2794	>160
Bond Strength to Concrete	ASTM D-4541	400 psi (substrate fails)
Compressive Strength	ASTM D-695	16,000 psi
Solids by Volume		100%
Adhesion	ASTM D-4541	400 psi
Hardness (Shore D)	ASTM D-2240	70
Flexibility (1/4: Cylindrical mandrel)	ASTM D-1737	Pass
Elongation	ASTM D-2370	9%
Tensile Strength	ASTM D-2370	7,000 psi
Static Coefficient of Friction*	ANSI B101.1	>0.6
Dynamic Coefficient of Friction - Wet*	ANSI A326.3	>0.42
Abrasion Resistance CS-10 Wheel, 1000 g Load, 1000 cycles	ASTM D-4060	27 mg
Flame Spread Index	ASTM E84	Class B (Type II)
VOC Content		0 g/L

*Dur-A-Flex flooring systems can be built to meet or exceed the requirements of Static or Dynamic Coefficient of Friction testing per installation. Contact your Dur-A-Flex territory sales manager or tech representative for more information on alternative textures, grit/grip additives, or smooth coatings for your specific environment. A sample should always be obtained and tested prior to purchase for any non-slip flooring system.

IMPORTANT!

Before using DUR-A-FLEX products, read and understand its accompanying Safety Data Sheet & Application Instructions for important safety information.

STANDARD TERMS AND CONDITIONS OF SALE, INCLUDING STANDARD WARRANTY APPLY - VISIT **DUR-A-FLEX.COM** FOR THE LATEST VERSION