

DUR-A-CRETE EPOXY GROUT MIXING GUIDE

This guide indicates the proper amount of Dur-A-Crete Sand and Pea Gravel required for mixing Dur-A-Crete Epoxy Grout. *Only use Dur-A-Crete Sand and ensure the Pea Gravel is washed and dried.*

Mix ratio per batch: 24 oz. of Dur-A-Glaze #4 Hardener and 48 oz. of Dur-A-Glaze #4 Resin or Shop Floor Resin. *The same amount of resin and hardener are used for all application thicknesses.*

Application Thickness (inches)	Dur-A-Crete Sand	Pea Gravel Size (inches)	Additional Pea Gravel (Gallons)	Square Feet per Batch	Cubic Feet per Batch
1/4	(1) 40 lb bag	-	-	20	0.41
1/2	(1) 40 lb bag	1/8	1 gallon	12	0.51
3/4	(1) 40 lb bag	1/8	1 gallon	8	0.51
1	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	6	0.51
1½	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	4	0.51
2	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	3	0.51
3+	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	2	0.51

Material Weight per Gallon

Material	Pounds per Gallon
Pea Gravel (1/8 & 3/8)	12
Dur-A-Crete Sand	13.5

Please contact your local Dur-A-Flex Technical Services Manager with any questions.